

# Technical Data Sheet

## Eastman™ Cellulose Acetate Butyrate (CAB-381-20)

### Applications

- Aerosol coatings
- Aerospace coatings
- Architectural coatings
- Auto oem
- Auto plastics
- Auto refinish
- Automotive
- Automotive parts & accessories
- Building materials
- Coil coatings
- Coil coatings-appliances
- Commercial printing inks
- Compensation film
- Consumer electronics
- Cosmetic ingredients - nails
- Exterior architectural coatings
- Flexographic printing inks
- General industrial coatings
- Graphic arts
- Gravure printing inks
- Industrial electronics
- Industrial maintenance
- Leather coatings
- Metal coatings
- Motorcycles
- Non-medical housings & hardware for elec
- Nonwoven substrates
- Other-transportation
- Outdoor signs
- Pack & carton coatings
- Packaging inks non food contact
- Paints & coatings
- Photographic imaging film
- Polymer modification
- Process additives
- Process solvents
- Protective coatings
- Rubber and plastic additives
- Screen printing inks
- Shelving solutions-retail
- Small appliances non-food contact
- Tools
- Touch screen
- Truck/bus/rv
- Wood coatings
- Wood furniture exterior

### Product Description

Eastman Cellulose Acetate Butyrate (CAB-381-20) is a cellulose ester with medium butyryl content and high ASTM(A) viscosity. Other than a higher viscosity and higher molecular weight, this cellulose ester shares the same general characteristics as CAB-381-0.1 and CAB-381-0.5. CAB-381-20 offers a combination of solubility and compatibility, moisture resistance, excellent surface hardness and good film strength. When CAB-381-20 is dissolved in appropriate solvents a clear, colorless solution is produced. CAB-381-20 is supplied as a dry, free-flowing powder.

Eastman CAB-381-20 is based on cellulose, one of the most abundant natural renewable resources, from trees harvested from sustainably managed forests. The calculated approximate bio-content value of 41% for Eastman CAB-381-20 was determined by using six bio-based carbon atoms per anhydroglucose unit divided by the total number of carbons per anhydroglucose unit. Although the value reported is not specifically measured for bio-carbon, it can be estimated based on typical partition data.

For applications that require food contact compliance, please refer to Eastman CAB-381-20, Food Contact.

## Typical Properties

Property	Typical Value, Units
<b>General</b>	
Viscosity <sup>a</sup>	
s	20
Poise	76
Acetyl Content	13.5 wt %
Butyryl Content	37 wt %
Hydroxyl Content	1.8 wt %
Moisture Content	3.0 max %
T <sub>g</sub> <sup>b</sup>	141 °C
Melting range	195-205 °C
Bulk Density	
Poured	336 kg/m <sup>3</sup> (21 lb/ft <sup>3</sup> )
Tapped	432 kg/m <sup>3</sup> (27 lb/ft <sup>3</sup> )
Specific Gravity	1.2
Acidity	
as Acetic Acid	<0.03 wt %
Ash Content	0.05 %
Refractive Index	1.475
Dielectric Strength	787-984 kv/cm (2-2.5 kv/mil)
Tukon Hardness	18 Knoop
Wt/Vol	
(Cast Film)	1.2 kg/L (10.0 lb/gal)
Heat Test	
@ 160°C for 8 hr	Tan melt

<sup>a</sup>Viscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

<sup>b</sup>Glass Transition Temperature

## Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

11/18/2019 6:52:14 AM

